









Product properties						
Format [mm]	Trendtime 3	Trendtime 4	Trendtime 6	Trendtime 8		Trendtime 9
	570 x 95 x 10,5	2010 x 160 x 13	2200 x 185 x 13	1882*x 190 x 15	1882*x 190 x 14	2380 x 233 x 15
Top layer:	≥ 2,5 mm	ca. 3,6 mm	ca. 3,6 mm	ca. 4,0 mm	ca. 3,0 mm	ca. 3,6 mm
Packaging	Pack: m ² /kg	20 Elements	9 Elements	9 Elements	8 Elements	9 Elements
		1,083 / 5,40	2,894 / 19,40	3,663 / 29,304	2,861 / 23,464	3,218 / 26,397
	Pallet: m ² /kg	36 Packs	32 Packs	32 Packs	32 Packs	32 Packs
		38,99 / 194,40	92,621 / 620,64	117,22 / 937,73	91,546 / 750,848	102,976 / 844,704
* Other formats possible. One short-length per packet possible				Notes		- cleaning and maintenance see instructions - technical changes reserved
Guarantee (according to Parador guarantee conditions)			25 years (domestic area)			

Product labelling	Tolerances (EN 13489)	
        	Admissible difference in length (± 0.1 %)	± 0,05 %
	Admissible difference in width (± 0.2 mm)	± 0,1 mm
	Squareness of the element (≤ 0.2 %)	≤ 0,05 %
	Longitudinal curvature along the element (≤ 0.1 %)	≤ 0,05 %
	Transverse curvature across the width (≤ 0.2 %)	≤ 0,08 %
	Height differences of elements (≤ 0.2 mm)	≤ 0,18 mm
	Moisture content at the time of first delivery (5-9%)	6 - 8 %

*not valid for smoked products.

Classification general product features											
		Test method	Rating								
	Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat								
	Effect of a furniture leg	EN 424	No visible changes								
	Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN ISO 10456	<table border="1"> <tr> <td>Trendtime 3</td> <td>0,070 m²K/W</td> </tr> <tr> <td>Trendtime 4 / 6</td> <td>0,087 m²K/W</td> </tr> <tr> <td>Trendtime 8</td> <td>0,100 m²K/W</td> </tr> <tr> <td>Trendtime 9</td> <td>0,093 m²K/W</td> </tr> </table>	Trendtime 3	0,070 m ² K/W	Trendtime 4 / 6	0,087 m ² K/W	Trendtime 8	0,100 m ² K/W	Trendtime 9	0,093 m ² K/W
Trendtime 3	0,070 m ² K/W										
Trendtime 4 / 6	0,087 m ² K/W										
Trendtime 8	0,100 m ² K/W										
Trendtime 9	0,093 m ² K/W										
	Formaldehyde (E1 = 0.1 ppm)	EN 717-1	≤ 0,05 ppm								
	Acoustical - Impact noise reduction	ISO 717-2	<table border="1"> <tr> <td>Trendtime 3</td> <td>- only suitable for all-over adhesion</td> </tr> <tr> <td>Trendtime 4 / 6 / 8 / 9</td> <td>18 dB (with Akustik-Protect 100)</td> </tr> </table>	Trendtime 3	- only suitable for all-over adhesion	Trendtime 4 / 6 / 8 / 9	18 dB (with Akustik-Protect 100)				
Trendtime 3	- only suitable for all-over adhesion										
Trendtime 4 / 6 / 8 / 9	18 dB (with Akustik-Protect 100)										
	Disposal	EAK-Code-number 20 01 38									

Classification surface characteristics					
		Test method	Rating		
			Natural oiled plus	Natural oiled plus (rough sawn)	Lacquer
	Slip resistance	EN 13893	μ ≥ 0,49	μ ≥ 0,53	μ ≥ 0,47
		CEN/TS 15676	99 (USRV)	99 (USRV)	29 SRT (SRV wet) 51 SRT (SRV dry)
	Reaction to fire, click-installation as a	EN 13501-1	D _{f1} s1		
	Reaction to fire, installation by all-	EN 13501-1	D _{f1} s1		
	Chemical resistance	EN 13442	Category 5 excepting ammonia solution (cat. 2)	Category 5 excepting ammonia solution (cat. 2)	Category 5
	Bond strength / Cross cutting test	ISO 2409	n.n.	n.n.	Category 0
	Slip resistance, inclined plane	DIN 51130	R10	R10	R 9

Changed:	QMB	File name:	20190901_PA_TDS_Parkett_Trendtime_EN
Date:	01.05.2013	Latest update at	www.parador.eu/service/catalogues-downloads/technical-data-sheets
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.09.2019

Free sorting according to EN 13489					
Assortment:	Wide plank				
Characteristics according to EN 1310:	Upper side of the floor board				
Design:	Trendtime 3		Trendtime 4		
Type of wood:	Oak	Oak	American cherry	American walnut	
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE	Quercus petraea Liebl., Quercus robur L. / QCXE	Prunus serotina Ehrh. / PRSR	Juglans nigra L. / JGNG	
Shortcut / sorting / date (internal):	ER-TT3-EI	ES-LH-TT4-EI	ER-TT4-KIR ami.	ER-TT4-SWN	
	Version 2 2012	Version 12 2016	Version 2 2012	Version 4 2013	
	A3	N4	N2	N2	N4
Grade:	Living	Living	Nature	Nature	Living
Sound sapwood	permitted	permitted	permitted	permitted	permitted
Knot (intergrown)	permitted: up to 30 mm	permitted: up to 40 mm	permitted	permitted: up to 15 mm	permitted
Falling out knot	permitted: up to 10 mm	permitted: up to 25 mm	permitted: up to 10 mm	permitted: up to 10 mm	permitted: up to 25 mm
Pinkknots	permitted	permitted: Cluster of knots	permitted	permitted	permitted
Filling	permitted	permitted	permitted	permitted	permitted
Slight cracks / hairline cracks	permitted: up to 1x100 mm	permitted: up to 1 x 200mm	not permitted	not permitted	not permitted
Sugar inclusions, mineral inclusions	-	-	permitted	-	-
Bark pocket	not permitted	not permitted	not permitted	not permitted	not permitted
Lightning cracks	permitted	permitted: in knots	not permitted	-	permitted: in knots
Slope of grain	no criterion	no criterion	no criterion	no criterion	no criterion
Healthy heart	-	not permitted	-	-	-
Medullary ray	permitted	permitted	permitted	-	-
Discoloration, colour variation	permitted: all colours	permitted: slight colour variations / slight discolorations	permitted: all colours	permitted: all colours	permitted: all colours
White streaks	permitted	-	-	-	-
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted
Non-visible parts					
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.					
Comment					
Maximum 3% of floor board are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.					

Changed:	QMB	File name:	20190901_PA_TDS_Parkett_Trendtime_Anhang_EN		
Date:	01.03.2013	Update:	www.parador.eu/service/catalogues-downloads/technical-data-sheets		
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.09.2019	Page 1 of 2	

Free sorting according to EN 13489					
Assortment:	Wide plank / 3-strip				
Characteristics according to EN 1310:	Upper side of the floor board / Upper side of the lamella				
Design:	Trendtime 6			Trendtime 8	Trendtime 9
Type of wood:	Oak (wide plank)	Beech (3-strip)	Oak (3-strip)	Oak	Oak
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE	Fagus sylvatica L. / FASY	Quercus petraea Liebl., Quercus robur L. / QCXE	Quercus spp. / QCXE	Quercus petraea Liebl., Quercus robur L. / QCXE
Shortcut / sorting / date (internal):	ER-LH-EI-N1/N2/N4	ER-L-BU	ER-L-EI	ER-TT8-EI	ER-L-EI
	Version 2 2018	Version 5 2014	Version 13 2019	Version 4 2015	Version 12 2016
	N4	N3	N3	N8	N3
Grade:	Living	Living	Living	Classic	Classic
Sound sapwood	permitted	-	permitted (also slightly discoloured)	permitted	permitted
Knot (intergrown)	permitted: up to 50 mm	permitted: up to 20 mm	not permitted	permitted	not permitted
Falling out knot	permitted: up to 25 mm	not permitted	not permitted	permitted	not permitted
Pinkknots	permitted	permitted	permitted: up to 15 mm	permitted	permitted: up to 15 mm
Filling	permitted	permitted	permitted	permitted	permitted
Slight cracks / hairline cracks	permitted	not permitted	not permitted	permitted	not permitted
Sugar inclusions, mineral inclusions	-	permitted: colour inclusions / slight discolorations	-	-	-
Bark pocket	not permitted	not permitted	not permitted	not permitted	not permitted
Lightning cracks	permitted: in knots	not permitted	permitted	permitted	permitted
Slope of grain	no criterion	no criterion	no criterion	no criterion	no criterion
Healthy heart	not permitted	permitted	-	permitted	-
Medullary ray	permitted	permitted	permitted	permitted	permitted
Discoloration, colour variation	permitted: light to medium brown colours	permitted: slight colour variations /	permitted: all colours	permitted: all colours	permitted: all colours
White streaks	Permitted	-	permitted	permitted	permitted
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted
Non-visible parts					
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.					
Comment					
Maximum 3% of floor board are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.					

Changed:	QMB	File name:	20190901_PA_TDS_Parkett_Trendtime_Anhang_EN
Date:	01.03.2013	Update:	www.parador.eu/service/catalogues-downloads/technical-data-sheets
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.09.2019
			Page 2 of 2